

0800333

https://www.phoenixcontact.com/us/products/0800333

Please be informed that the data shown in this PDF document is generated from our online catalog. Please find the complete data in the user documentation. Our general terms of use for downloads are valid.



Shrink sleeve, Roll, yellow, unlabeled, can be labeled with: THERMOMARK E.300 (D)/600 (D), THERMOMARK ROLLMASTER 300/600, THERMOMARK ROLL X1, THERMOMARK ROLL, THERMOMARK ROLL 2.0, THERMOMARK W, THERMOMARK X1.2, unperforated, mounting type: slide-on, cable diameter range: 4.2 ... 12.7 mm, Number of individual labels: 1, roll length: 80 m, text field height: 20 mm, text field width: 80000 mm

#### Product description

The continuous shrink sleeves in the WMS... product family can be assembled to create individual marker lengths using the THERMOMARK E. CUTTER or E.CUTTER/P. After the printing, assembly, and applying process, you have the option of shrinking the marked shrink sleeves by applying heat manually and thus fixing them on the cable/wire.

#### Your advantages

- · Permanent and captive identification of single-core wires, wires, cables, pneumatic hoses, and other cylindrical objects
- High flexibility, as individual marker lengths ranging from 3.45 mm ... 2000 mm (0.14" ... 78.7") can be realized in combination with the cutter and perforation cutter
- · As an option, the sleeves can be shrunk by applying heat manually to fix the sleeve in position
- High diameter coverage with a shrink ratio of 3:1
- · Widely used and proven worldwide in control cabinet and machine building, the oil and gas industry, and the railway industry

#### Commercial data

Item number	0800333
Packing unit	1 pc
Minimum order quantity	1 pc
Note	Made to order (non-returnable)
Sales key	BG14
Product key	BG2216
Catalog page	Page 227 (C-3-2019)
GTIN	4046356626125
Weight per piece (including packing)	1,094 g
Weight per piece (excluding packing)	840 g
Customs tariff number	39173200
Country of origin	CN



https://www.phoenixcontact.com/us/products/0800333



### Technical data

#### Notes

Note on application	For the THERMOMARK ROLL and THERMOMARK ROLL 2.0 roll printers, this material can only be processed with an external media hub.
Material information	The specified minimum wire diameter of the shrink sleeve refers to its use as a marking material and does not guarantee any insulation characteristics once shrunk.
	Depending on the processed material batch, as well as the storage and processing conditions, the maximum insertable wire diameter may be reduced.

# Product properties Product type

Туре	Shrink sleeve
Data management status	
Article revision	03
Marking	
Number of individual labels	1
Identification technology	Thermal transfer for rolls

Shrink sleeve

#### **Dimensions**

Width	20 mm
Text field width	80000.00 mm
Text field height	20.00 mm
Length of roll	80.00 m
External dimensions	
Outside diameter	4.2 mm 12.7 mm

#### Material specifications

RoHS compliant	yes
Color	yellow (RAL 1018)
Material	Polyolefine
Base element material	polyolefine
Shrink rate	3:1
Components	halogen-free
Shrink temperature	> 85 °C

#### Cable/line

External cable diameter	4.2 mm 12.7 mm

### Environmental and real-life conditions



0800333

https://www.phoenixcontact.com/us/products/0800333

Result	Test passed
cratch test for the determining scratch resistance	
Specification	DIN EN ISO 1518-1:2019-10 (following)
Requirements	≥ 5 N
Result	Test passed
esafilm test	
Specification	DIN EN ISO 2409:2013 (following)
Result	Test passed
V resistance	
Specification	ISO 4892-2:2013-03 (following)
Result	Test passed
Test duration	96 h
	50 H
emperature resistance	
Specification	ANSI/UL 969-2018:03 (following)
Test duration	240 h
Rating 125 °C (150 °C)	Test passed
pe resistance of inscriptions	
Specification	DIN EN 61010-1 (VDE 0411-01):2020-03
	DIN EN 62208 (VDE 0660-511):2012-06 (in parts)
Isopropyl [CAS No. 67-63-0]	Test passed
n-Hexane [CAS No. 110-54-3]	Test passed
Water + Petroleum ether [CAS No. 64742-82-1]	Test passed
Sodium hydroxide 0.1 mol/l [CAS No. 1310-73-2]	Test passed
Ethanol (99 %) [CAS No. 64-17-5]	Test passed
Acetone (99 %) [CAS No. 67-64-1]	Test passed
Specification	ISO 175:2010 (following)
Test duration	168 h
Sodium hydroxide 0.1 mol/l [CAS No. 1310-73-2]	Test passed
Ethanol (99 %) [CAS No. 64-17-5]	Test passed
Acetone (99 %) [CAS No. 67-64-1]	Test passed
Diesel [CAS No. 68476-34-6]	Test passed
IRM 901	Test passed
IRM 902	Test passed



0800333

https://www.phoenixcontact.com/us/products/0800333

Testing in a condensation		

Specification	DIN 50018:2013-05
Result	Test passed
Climate level	AHT 1.0 S
Cycles	2

#### Salt spray test

Specification	DIN EN 60068-2-11:2000-02
Result	Test passed
Test duration	96 h

#### Ambient conditions

Ambient temperature (operation)	-55 °C 125 °C
Recommended storage conditions	23 °C/50 % relative humidity. Storage in a dry and dark place in the original packaging is recommended.
Recommended ambient temperature (storage/transport)	23 °C
Recommended humidity (storage/transport)	50 %
Shelf life	5 years

### Standards and regulations

Wipe resistance	DIN EN 61010-1 (VDE 0411-1)
-----------------	-----------------------------

### Mounting

Mounting type	slide-on
---------------	----------



0800333

https://www.phoenixcontact.com/us/products/0800333

### **Approvals**

To download certificates, visit the product detail page: https://www.phoenixcontact.com/us/products/0800333



**CSA** 

Approval ID: 252259



cULus Recognized

Approval ID: E310982\_Vol2\_Sec1



0800333

https://www.phoenixcontact.com/us/products/0800333

## Classifications

UNSPSC 21.0

#### **ECLASS**

27281102
27281102
27281102
EC001530

39131500



0800333

https://www.phoenixcontact.com/us/products/0800333

### Environmental product compliance

#### EU RoHS

Fulfills EU RoHS substance requirements	Yes, No exemptions
EU REACH SVHC	

Phoenix Contact 2024 © - all rights reserved https://www.phoenixcontact.com

Phoenix Contact USA 586 Fulling Mill Road Middletown, PA 17057, United States (+717) 944-1300 info@phoenixcon.com